CI/SfB (43) Yq

MAY 2025
(SUPERSEDES MARCH 2021)
PRODUCT DATA SHEET

ARDEX AF 2575 PLUS

One Component Heavy Duty Adhesive

Features

- No mixing required, ready for use and resealable
- High temperature resistance, for use in areas of direct sunlight and with underfloor heating
- Moisture, weather and water resistant
- Ideal for installing safety flooring in a wet room
- Suitable for installing LVT to walls
- Very high bond strength, for use in high load areas
- Suitable for internal and external use
- Very low emissions
- Solvent free
- Covers up to 23m^2

bsi ISO 9001 Quality Management Systems CERTIFIED Reg No. FM 01207
ISO 14001 Environmental Management CERTIFIED EMS 565427
ISO 45001 Occupational Health and Safety Management CERTIFIED OHS 628374

ARDEX UK LIMITED
Homefield Road, Haverhill, Suffolk CB9 8QP UK.
Telephone: +44 (0)1440 714939
Fax: +44 (0)1440 716640
Email: info@ardex.co.uk
ARDEX online: www.ardex.co.uk

ARDEX AF 2575 PLUS

Component Adhesive Heavy Duty One

DESCRIPTION
ARDEX AF 2575 PLUS is a solvent free, low odour, wet bond MS Polymer based floorcovering adhesive. ARDEX AF 2575 PLUS is protected from biodegradation and has good resistance to plasticiser migration.

ARDEX AF 2575 meets the requirement guidelines for the EMICODE licence 'EC1 PLUS', achieving very low emission limits.

USE
ARDEX AF 2575 PLUS is ideal for installing all types of floorcoverings, including luxury vinyl tiles, sheet vinyl, and can be used with all ARDEX Latex and Water-Based Levelling and Smoothing Compounds in both commercial and domestic locations. ARDEX AF 2575 PLUS is suitable for use with chairs fitted with castor wheels.

PRIMING
Priming is not required.

SUBSTRATE PREPARATION
The subfloor must contain an effective damp proof membrane and be dry, with an equilibrium relative humidity of 75% or below. Where an effective damp proof membrane is absent, or the relative humidity of the subfloor is above 75% RH, consult the ARDEX Moisture Control brochure or contact ARDEX Technical Services for the correct product selection.

The subfloor must be hard, clean, free from barrier materials, sound and smooth in accordance with the relevant clauses of
BS 8203 and BS 8204.

Any dust should be removed using suitable vacuum equipment, prior to applying ARDEX AF 2575, as it can affect both the coverage and performance of the adhesive.

Uneven subfloors should be levelled with the appropriate ARDEX Latex or Water-Based Levelling and Smoothing Compound e.g. ARDITEX NA or ARDEX K 39.

ARDEX ARDURAPID A 45 Rapid Drying and Hardening Internal Repair Mortar can be used for repairs to the subfloor/stairs etc. up to 50mm thick, in accordance with the product data sheet.

Joints, nail holes and imperfections in plywood, or minor surface damage to existing levelling and smoothing compounds i.e. footprints or trowel marks, may be pre-smoothed and levelled prior to the application of ARDEX AF 2575 PLUS, using ARDEX FEATHER FINISH in accordance with the product
data sheet.

Fabricated underlays such as flooring grade plywood, (SP101) should be installed where required over existing timber bases.
Wood-based fabricated underlays should be suitable for the floorcovering and be at the equilibrium moisture content they will have in service at the time they are covered.

MIXING
ARDEX AF 2575 PLUS is ready for use and does not require mixing.

APPLICATION
The installation area and subfloor should be kept at the appropriate temperature as specified by the floorcovering manufacturer and the relevant clauses of BS 8203. These temperatures need to be maintained 48 hours prior to installation, during installation, and 48 hours after installation.

ARDEX AF 2575 PLUS should be applied evenly to the suitably prepared substrate using the appropriate serrated trowel, held approximately at a 60 degree angle to the subfloor to maximise coverage and avoid forming pools of adhesive.

Floorcoverings should be applied directly into the wet adhesive on absorbent backgrounds after the airing time, between 5-30 minutes depending on ambient conditions.

Allowing the adhesive to air will improve early stage grab.

Only apply sufficient adhesive that can be covered within the working time, usually 35 minutes. Periodically check that the adhesive has transferred to the rear of the floorcovering.

Remove any air pockets with a cork board or rubbing tool whilst the adhesive is still wet, and roll the floorcovering with a 68kg roller and/or a smoothing tool if required.

Roll from side to side first and then end to end. Rolling will ensure good overall contact and minimise the potential for adhesive serration grin through.

Some floorcoverings may benefit from further rolling/smoothing. Heat welding should only commence once the adhesive has dried sufficiently.

Do not allow the floor to be wet cleaned immediately after the floorcovering has been installed. Allow significant time for the adhesive bond to develop before wet cleaning commences, typically 48 hours at 20°C.

When applying adhesive onto the substrate, ensure that any adhesive which is surplus to requirements, and has been moved across the subfloor, is not placed back into the container. It should be placed into an alternative container for safe, easy disposal. This will avoid possible contamination issues.

UNDERFLOOR HEATING
Underfloor heating systems should be commissioned in accordance with the heating manufacturer's instructions; if comment cannot be found then the guidance given in BS 8203 and BS 8204 should be followed.

Thermal cycling of the subfloor will require raising the temperature of the substrate slowly, usually 5°C a day, to full operating temperature, held for a defined period, and slowly brought back down, usually 5°C a day, so that any shrinkage that is likely to take place occurs before the floorcovering is installed.

If moisture tests are required to verify the relative humidity of the substrate, the underfloor heating system should be switched off for 48 hours prior to testing.

If moisture testing is not required, or after the tests are completed, the heating system should be stabilised to room temperature, but not below 15°C, before installing the floorcovering.

The surface of the substrate can then be repaired/ smoothed with the appropriate ARDEX product and allowed to dry.

The floorcovering should be allowed to acclimatise to the substrate temperature before installation with ARDEX AF 2575 PLUS.

After installation allow at least 48 hours of constant temperature for the adhesive to properly cure, before slowly increasing the temperature up to the normal operating temperature of the area. Do not subject the floor to static or dynamic loads, loaded trolleys, etc., or move fixtures, furniture, etc., onto the flooring until the adhesive has fully set, typically 48 hours at 20°C.

HIGH TEMPERATURE
ARDEX AF 2575 PLUS is suitable for use over underfloor heating systems and is classified as high temperature resistant. ARDEX AF 2575 PLUS is suitable for use in areas of high solar gain such as conservatories and southerly facing aspects. The surface floor temperature must not exceed 50°C for prolonged periods.

Consult the floorcovering manufacturer for detailed guidance.

ARDEX AF 2575 PLUS

One Component Heavy Duty Adhesive

CLEANING
Remove spills or seepage through joints with ARDEX Heavy Duty Cleaning Wipes.

Aggressive cleaning agents should only be used with the permission of the floorcovering manufacturer.

PACKAGING
ARDEX AF 2575 PLUS is packed in plastic tubs 7kg net weight.

COVERAGE
See table below.

The actual coverage achieved in practice is affected by application technique, as well as the texture and absorbency of the subfloor.

STORAGE
ARDEX AF 2575 PLUS must be stored in unopened packaging, clear of the ground in cool dry conditions and be protected from excessive draught. If stored correctly, as detailed above, the shelf life of this product is 18 months from the date shown on the packaging.

PRECAUTIONS
ARDEX AF 2575 PLUS is non-hazardous in normal usage, however, good hygiene practices should be followed.

Avoid contact with skin; wash off with soap and water before drying takes place. In case of contact with eyes, rinse carefully and thoroughly with water and seek medical advice. In case of ingestion seek medical assistance.

Consult the relevant Health & Safety Data Sheets for further information.

For the latest technical or health and safety information on this product, consult the current product or health and safety data sheet online at: **www.ardex.co.uk**

WORDING AND TERMINOLOGY

Airing Time
The time the adhesive must be left open before applying the floorcovering.
5-30 minutes*

Working Time
The time in which the adhesive can receive the floorcovering, after the initial airing time. Up to 35 minutes*

Open Time
The combination of airing and working time. Up to 40 minutes*

*depending on the absorbency of the subfloor and ambient conditions,
(20°C & 65% RH).

The guidance from the floorcovering manufacturer should always be followed if different from the information contained in this Technical Data Sheet.

NOTE: The information supplied in our literature or given by our employees is based upon extensive experience and, together with that supplied by our agents or distributors, is given in good faith in order to help you. Our Company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products; however, as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.

Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may affect specific installation recommendations.

Flooring Type	Trowel Size	Coverage
LVT, Vinyl, CV flooring, Rubber flooring	A1	Up to 23m²
LVT, Vinyl, CV flooring, Rubber flooring	A2	Up to 19m²
Rubber flooring with sanded back > 3.2	B1	Up to 16m²

TECHNICAL ADVICE HELPLINE
01440 714939
ARDEX online: www.ardex.co.uk